

Test Report

Number: GZHT01812927

Applicant: GUANGZHOU MOS TRADING CO.,LIMITED
NO.46,GUANGXING ROAD,NANSHA,GUANGZHOU
CITY,GUANGDONG PROVINCE,CHINA 511458
广州晴晴家具贸易有限公司
广州市南沙区广兴路 46 号


Date: Aug 09, 2017

Attn: 徐锋

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 100% Polypropylene
Material : Outdoor Olefin Fabric
Finishing : -
End Uses : Outdoor Cushion/ Outdoor Pillow
Season : -
Colour : Lakeside
Style No. : #15260502
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Prepared And Checked By:
For Intertek Testing Services Guangzhou Ltd.



Lin Lin
General Manager

SuQ / abbeyluo



Page 1 Of 4

Test Report

Number: GZHT01812927

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : Aug 01, 2017

Date Final Information Confirmed: -

Conclusion:

Determination Of Formaldehyde (Part 1)	M
Colour Fastness To Rubbing	M
Colour Fastness To Light	M
Seam Slippage As Received	M*
Abrasion Resistance	F
Pilling Resistance As Received	#

Note : C = Conform Label

M = Meet Applicant's Requirement

F = Fail To Meet Applicant's Requirement

= No Comment

* = See Remark


M* = Commercially Acceptable

F* = Commercially Unacceptable

N/A = Not Applicable

- = Did Not Perform

Prepared And Checked By:
For Intertek Testing Services Guangzhou Ltd.



Lin Lin
General Manager

SuQ / abbeyluo



Page 2 Of 4

Test Report

Number: GZHT01812927

Tests Conducted (As Requested By The Applicant)

1 Determination Of Formaldehyde (Part 1) : Free And Hydrolyzed Formaldehyde (ISO 14184-1:2011):

	Not Detectable	<u>Applicant's Requirement</u> 100 µg/g
--	----------------	--

Remark : Detection limit = 5 ppm

2 Colour Fastness To Rubbing (ISO 105 X12-2016):

		<u>Applicant's Requirement</u>
Dry	4-5	4
Wet	4-5	4

3 Colour Fastness To Light (ISO 105 B02-2014, Exposure Cycle A1, Xenon-Arc Lamp):

		<u>Applicant's Requirement</u>
Grade	Above 6	5-6

4 Seam Slippage As Received (ISO 13936-2:2004, Tensile Testing Machine, CRE):

(I) The Mean Seam Opening After Reducing Load To 5 N From 120 N Load

// To Warp	1.5 mm
// To Weft	1.5 mm

Remark : N = Newton

5 Abrasion Resistance (ISO 12947-2:1998, Martindale Abrasion And Pilling Tester, 9 kPa Total Weight):

		<u>Applicant's Requirement</u>
<u>Resistance</u>		
Face Side	13000 rubs	15,000 Rubs

SuQ / abbeyluo

Test Report

Number: GZHT01812927

Tests Conducted (As Requested By The Applicant)

6 Pilling Resistance As Received (ISO 12945-2:2000, Martindale Abrasion & Pilling Tester, 415 g Total Loading):

After 125 Revolutions

Grade 4

After 500 Revolutions

Grade 4

After 1,000 Revolutions

Grade 4

After 2,000 Revolutions

Grade 4

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

SuQ / abbeyluo

Page 4 Of 4