

Test Report

Number: GZHT01812561

Applicant: GUANGZHOU MOS TRADING CO.,LIMITED
NO.46,GUANGXING ROAD,NANSHA,GUANGZHOU
CITY,GUANGDONG PROVINCE,CHINA 511458
广州晴晴家具贸易有限公司
广州市南沙区广兴路 46 号


Date: Aug 09, 2017

Attn: 徐锋

Sample Description As Declared :

No. Of Sample : One
Fibre Content : 100% Polypropylene
Material : Woven Fabric, Outdoor 100% Olefin Fabric
Finishing : -
End Uses : Outdoor Cushion/Outdoor Pillow
Season : -
Colour : Amazon
Style No. : #15230462
Order No./PO No. : -
Standard : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Prepared And Checked By:
For Intertek Testing Services Guangzhou Ltd.



Lin Lin
General Manager

RH / liangyt



Page 1 Of 4

Test Report

Number: GZHT01812561

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : Jul 31, 2017

Date Final Information Confirmed: -


Conclusion:

Determination Of Formaldehyde (Part 1)	M
Colour Fastness To Light	M
Colour Fastness To Rubbing	M
Seam Slippage As Received	M
Pilling Resistance As Received	M
Abrasion Resistance	M

Note : C = Conform Label
M = Meet Applicant's Requirement
F = Fail To Meet Applicant's Requirement
= No Comment
* = See Remark

M* = Commercially Acceptable
F* = Commercially Unacceptable
N/A = Not Applicable
- = Did Not Perform

Prepared And Checked By:
For Intertek Testing Services Guangzhou Ltd.



Lin Lin
General Manager

RH / liangyt



Page 2 Of 4

Test Report

Number: GZHT01812561

Tests Conducted (As Requested By The Applicant)

1	Determination Of Formaldehyde (Part 1) : Free And Hydrolyzed Formaldehyde (ISO 14184-1:2011):		<u>Applicant's Requirement</u> Max 100 µg/g
		Not Detectable	
2	Colour Fastness To Light (ISO 105 B02-2014, Exposure Cycle A1, Xenon-Arc Lamp):		<u>Applicant's Requirement</u> 5-6
	Grade	Above 6	
3	Colour Fastness To Rubbing (ISO 105 X12-2016):		<u>Applicant's Requirement</u>
	Dry	4-5	4
	Wet	4-5	4
4	Seam Slippage As Received (ISO/DIS 13936-2:1998, Tensile Testing Machine, CRE):		<u>Applicant's Requirement</u>
(I)	The Mean Seam Opening After Reducing Load To 5 N From 120 N Load		
	// To Warp	1.9 mm	6 mm
	// To Weft	1.7 mm	6 mm

Remark : N = Newton

RH / liangyt

Page 3 Of 4

Test Report

Number: GZHT01812561

Tests Conducted (As Requested By The Applicant)

5 Pilling Resistance As Received (ISO 12945-2:2000, Martindale Abrasion & Pilling Tester, 415 g Total Loading):

<u>After 2,000 Revolutions</u>		<u>Applicant's Requirement</u>
Grade	4	3-4

6 Abrasion Resistance (ISO 12947-2/3/4:1998, Martindale Abrasion And Pilling Tester, 9 kPa Total Weight):

<u>Resistance</u>		<u>Requirement</u>
Face Side	Over 15000 Cycles	15000 Cycles

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

RH / liangyt

Page 4 Of 4