

TEST REPORT

Technical Report: (9317)265-0029

Page 1 of 6
October 09, 2017



Report Number
(9317)265-0029

**Bureau Veritas Consumer Products Services
(Guangzhou) Co., Ltd**

No. 183, Shinan Road, Meilin Plaza, Dongchong, Nansha,
Guangzhou, Guangdong Province, China 511453
Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303
Email: BVCPS_pyinfo@cn.bureauveritas.com
Website: cps.bureauveritas.com

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/cps> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



**BUREAU
VERITAS**

TEST REPORT

**TO : AXROMA TECHNICAL TEXTILES CO LTD
NO.25 YUZHOU(SOUTH) HAIZHOU
DEVELOPMENT ZONE LIANYUNGANG JS
CHINA**

ATTN : TYPHOON XU

LAB NO.: (9317)265-0029
FORM NO.: /
DATE IN: Sep 22, 2017
DATE OUT: OCT 09, 2017
NO. OF WORKING DAYS: /
PAGE 2 OF 6

OVERALL RATING

PASS	<u> X </u>
FAIL	<u> </u>
DATA	<u> </u>

Vendor:	/	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	#501.804
Sample Description:	ST.TROPEZ	Style Description:	/
Color:	LAKESIDE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	CUSHION, PILLOW, SOFA
SKU:	/	Age Group:	/

Product Category	FABRIC
Test Requested	SEE TEST PROPERTY
Previous Report No.	/

Submitted Fiber Content	100% OLEFIN
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
FLAMMABILITY BS 5852	X			

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (GUANGZHOU) CO., LTD



JOEIE TSANG
GENERAL MANAGER

TEST RESULTS

TEST PROPERTY

REQUIREMENTS

FLAMMABILITY BS 5852

TEST INFORMATION & EXECUTIVE SUMMARY

Evaluation To: Flammability in comparison with the requirements of: -
1. The Furniture and Furnishings (Fire) (Safety) Regulations 1988. S.I. No. 1324(amended 1989, 1993 and 2010), Schedule 4, Part I, Cigarette test for cover fabrics.
2. The Furniture and Furnishings (Fire) (Safety) Regulations 1988. S.I. No. 1324(amended 1989, 1993 and 2010), Schedule 5, Part I, Match test for cover fabrics.

Standards As specified in above standard(s) and incorporated with
Employed: using ignition source 0 and 1 of BS 5852:Part 1:1979.

Condition prior Prior to testing the fabric was cleansed using a water-soak
to testing: procedure as described in BS 5651:1978(As specified), line dried and conditioned in indoor ambient conditions for 72 hours and then in a standard atmosphere having a temperature of 20±5°C and a relative humidity of 50±20% RH for a minimum of 16 hrs.

Conclusions: The cover sample supplied MEETS the requirements of The Furniture and Furnishings (Fire) (Safety) Regulations 1988, S.I. No. 1324(amended 1989, 1993 and 2010), Schedule 4, Part I and Schedule 5, Part I, when using ignition source 0 & 1 of BS 5852:Part 1:1979.

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
----------------------	---------------------	---------------------

SUMMARY OF EXAMINATION

Introduction:

An examination was requested to ascertain compliance with the requirement(s) as detailed on page one of this report. The following clauses were considered applicable and our findings were as follows:

1. The Furniture and Furnishings (Fire) (Safety) Regulations 1988. S.I. No. 1324 (amended 1989, 1993 and 2010), Schedule 4, Part I, Ignitability test for Cover fabrics. Cigarette Test (Ignition Source 0)		
Specimen number	1	2
Ignition (I) / Did not ignite (DNI) / Ignite but extinguished (IBE) / Surface flash burn (SFB)	DID NOT IGNITE	DID NOT IGNITE
Time for cigarette consumed	26 min 48 sec	27 min 04 sec
Smouldering	NIL, 0 sec	NIL, 0 sec
Flaming ceased	NIL, 0 sec	NIL, 0 sec
Smoking	NIL, 0 sec	NIL, 0 sec
Afterglow	NO	NO
Cover char splitting	NA	NA
Final examination of progressive smouldering	/	/
Criteria of failure	/	

* Fails to smoulder its complete length

2. The Furniture and Furnishings (Fire) (Safety) Regulations 1988. S.I. No. 1324, (amended 1989, 1993 and 2010), Schedule 5, Part I, Ignitability test for Cover fabrics. Match Test (Ignition Source 1)		
Specimen number	1	2
Ignition (I) / Did not ignite (DNI) / Ignite but extinguished (IBE) / Surface flash burn (SFB)	DNI	DNI
Smouldering ceased	NIL, 0 sec	NIL, 0 sec
Flaming ceased	NIL, 0 sec	NIL, 0 sec
Smoking	YES, 7 sec	YES, 8 sec
Afterglow	NO	NO
Cover char splitting	NO	NO
Final examination of progressive smouldering	/	/
Criteria of failure	/	

ANNEX I: SUBMISSION DESCRIPTION

Sample Description: Cover fabric

Details of sample: /

Material Identification: Not given.

ANNEX II: ADDITIONAL COMMENTS

- I All the test results contained on this report are relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.
- II BV can take no responsibility for the accuracy of the reference/descriptions supplied by the client.
- III NA = Not applicable on this evaluation.
- IV In the cigarette test, the submitted sample was tested in combination with Combustion Modified High Resilient (CMHR) Foam as specified in Schedule 5 Part II of the Regulations.
- V In the Match test, the submitted sample was tested in combination with standard worse case scenario non-flame retardant conventional polyurethane foam as specified in Schedule 5 Part I of the Regulations.
- VI In the interests of safety all tested samples, along with any residue of failed samples will be disposed of immediately.
