



**BUREAU  
VERITAS**

# TEST REPORT

**Technical Report:** (9322)185-1521

Page 1 of 4  
September 21, 2022



**Report Number  
(9322)185-1521**

**Bureau Veritas Consumer Products Services  
(Guangzhou) Co., Ltd**  
No. 183, Shinan Road, Meilin Plaza, Dongchong,  
Nansha, Guangzhou, Guangdong Province, China  
511453  
Tel: (86) 20 2290 2088 Fax: (86) 20 3490 9303  
Email: BVCPS\_pyinfo@cn.bureauveritas.com  
Website: cps.bureauveritas.com

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



**BUREAU  
VERITAS**

# TEST REPORT

**TO : AXROMA TECHNICAL TEXTILES CO LTD  
NO.25 YUZHOU(SOUTH) HAIZHOU  
DEVELOPMENT ZONE  
LIANYUNGANG, JS,  
CHINA**

**LAB NO.:** (9322)185-1521  
**FORM NO.:** /  
**DATE IN:** Jul 04, 2022  
**DATE OUT:** Sep 21, 2022  
**NO. OF WORKING DAYS:** /  
**PAGE 2 OF 4**

**ATTN : LEO ,**

<b><u>OVERALL RATING</u></b>	
<b>PASS</b>	<u>    X    </u>
<b>FAIL</b>	<u>          </u>
<b>DATA</b>	<u>          </u>

<b>Vendor:</b>	/	<b>Agent:</b>	/
<b>Fabric Supplier/Mill:</b>	/	<b>Factory/Manufacturer:</b>	/
<b>P.O. No.:</b>	/	<b>Style No.:</b>	15835515/502.805
<b>Sample Description:</b>	100% SOLUTION-DYED OLEFIN	<b>Style Description:</b>	/
<b>Color:</b>	MEDOC PEACOCK	<b>Country of Origin:</b>	/
<b>Claimed Fabric Weight:</b>	/	<b>Claimed Fabric Count:</b>	/
<b>Yarn Size:</b>	/	<b>Submitted Size:</b>	/
<b>Size Range:</b>	/	<b>FPU No.:</b>	/
<b>GPU No.:</b>	/	<b>End Use:</b>	OUTDOOR CUSHION/ PILLOW/ UPHOLSTERY
<b>SKU:</b>	/	<b>Age Group:</b>	/

<b>Product Category</b>	FABRIC
<b>Test Requested</b>	SEE TEST PROPERTY
<b>Previous Report No.</b>	/

<b>Submitted Fiber Content</b>	100% OLEFIN
<b>Actual Fiber Content</b>	/
<b>Suggested Fiber Content</b>	/
<b>Submitted Care Instruction(s)</b>	/
<b>Client Expected Care Instruction</b>	/
<b>Suggested Care Instruction(s)</b>	/



**BUREAU  
VERITAS**

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER REPELLENCY: SPRAY TEST	X			
COLORFASTNESS TO LIGHT	X			

**TECHNICAL  
QUESTIONS** (86)20-22902088  
bvcps\_pyinfo@cn.bureauveritas.com

**GENERAL  
INFORMATION** (86)20-22902088  
bvcps\_pyinfo@cn.bureauveritas.com

**SIGNATURES** Bureau Veritas Consumer Products Services  
(Guangzhou) Co., Ltd

Quan Peng  
Operation Manager



**BUREAU  
VERITAS**

**TEST RESULTS**

**TEST PROPERTY**

**REQUIREMENTS**

**WATER REPELLENCY: SPRAY TEST** (AATCC 22-17)

AS RECEIVED (RATING)                      100.0    MIN. 90

SPRAY RATING:

- 100 - NO STICKING OR WETTING OF UPPER SURFACE
- 90 - SLIGHT RANDOM STICKING OR WETTING OF UPPER SURFACE
- 80 - WETTING OF UPPER SURFACE AT SPRAY POINTS
- 70 - PARTIAL WETTING OF WHOLE OF UPPER SURFACE
- 50 - COMPLETE WETTING OF WHOLE OF UPPER SURFACE
- 0 - COMPLETE WETTING OF WHOLE UPPER AND LOWER SURFACE

**COLORFASTNESS TO LIGHT** (AATCC 16.3-20, OPTION 3, WATER COOLED XENON-ARC LAMP, 1000 & 1200 AFU)

COLOR CHANGE (1000 AFU)	4.0	MIN. GRADE 3.5
COLOR CHANGE (1200 AFU)	4.0	MIN. GRADE 3.5

**COLORFASTNESS RATING  
COLOR CHANGE**

- 5 NEGLIGIBLE OR NO CHANGE
- 4 SLIGHTLY CHANGED
- 3 NOTICEABLY CHANGED
- 2 CONSIDERABLY CHANGED
- 1 MUCH CHANGED

**COLORFASTNESS RATING  
COLOR STAIN  
SELF STAINING**

- 5 NEGLIGIBLE OR NO STAINING
- 4 SLIGHTLY STAINED
- 3 NOTICEABLY STAINED
- 2 CONSIDERABLY STAINED
- 1 HEAVILY STAINED